

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM, OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

- AN - 1997-209397 [19]
 AP - JP19950220370 19950829
 CPY - TEIJ
 DC - A23
 FS - CPI
 IC - C08G64/30 ; C08G64/40
 MC - A05-E06A A10-D05 A10-G01A A10-G01B A11-A01 A11-A03 A11-B07C
 PA - (TEIJ) TEIJIN LTD
 PN - JP9059367 A 19970304 DW199719 C08G64/30 001pp
 PR - JP19950220370 19950829
 XA - C1997-067478
 XIC - C08G-064/30 ; C08G-064/40
 AB - J09059367 The prepn. of a polycarbonate (PC) resin comprises kneading PC in the presence of N₂ which is fed at a speed of 0.1-20 normal litre based on 100 g. PC, by an extruder having an evacuated vent port and then treating under vacuum.
 - Pref. the PC is that prepd. by fusion-polymerising an aromatic dihydroxy cpd. with an aromatic dicarbonate. The PC is prepd. by fusion-polymerising with 0.0000001-0.001 equiv. per mol. of an aromatic dihydroxy cpd., of an alkali metal cpd. and/or alkali earth metal cpd. and a N-contg. basic cpd. as polymerising catalysts and added 0.01-500 ppm. of a stabiliser. The stabiliser is ammonium sulphonate and/or phosphonium sulphonate, the ester, the ammonium salt and/or the phosphonium salt of dodecylbenzene sulphonate or the ester, the ammonium or the phosphonium of p-toluene sulphonic acid and/or the ester, ammonium salt or phosphonium salt of benzene sulphonic acid. PC is kneaded in N₂ at 200-350 deg. C for 0.1-100 sec. and then treated at 0.1-700 mmHg.
 - ADVANTAGE - The obtd. PC resin contains only slight impurities, esp. volatile impurities and, therefore has good thermal stability, hue stability and hydrolysis resistance.
 - (Dwg.0/0)
 IW - PREPARATION POLYCARBONATE RESIN THERMAL STABILISED COMPRISE KNEAD POLYCARBONATE PRESENCE NITROGEN FEED SPECIFIC SPEED EXTRUDE HEAT VACUUM
 IKW - PREPARATION POLYCARBONATE RESIN THERMAL STABILISED COMPRISE KNEAD POLYCARBONATE PRESENCE NITROGEN FEED SPECIFIC SPEED EXTRUDE HEAT VACUUM
 NC - 001
 OPD - 1995-08-29
 ORD - 1997-03-04
 PAW - (TEIJ) TEIJIN LTD
 TI - Prepn. of polycarbonate resin having good thermal stability - comprises kneading polycarbonate in presence of nitrogen, fed at specific speed, by extruder then heating under vacuum
 A01 - [001] 018 ; P0862 P0839 F41 F44 D01 D63 ;
 - [002] 018 ; R00470 G1161 G1150 G1149 G1092 D01 D11 D10 D19 D18 D32 D50 D76 D93 F32 F30 ; R06918 G1296 D01 D19 D18 D32 D50 D63 D76 D93 F44 ; H0022 H0011 ; H0293 ; L9999 L2528 L2506 ; L9999 L2197 L2186 ; S9999 S1547 S1536 ; L9999 L2653 L2506 ;
 - [003] 018 ; B9999 B4682 B4568 ; N9999 N7272 ; N9999 N5970-R ; N9999 N6439 ; N9999 N6757 N6735 N6655 ; K9949 ; N9999 N6360 N6337 ; R9999 R4499 R4466 ; R9999 R3690-R ; R9999 R4706-R R4569 ;

B9999 B3678 B3554 ; N9999 N6597 N6586 ; ND07 ; N9999 N6826 N6655 ;
B9999 B3725 B3690 ;
- [004] 018 ; D01 D11 D10 D18-R D19 D18 D32 D76 D61-R D93 1A-R Na 1A
2A-R ; C999 C102 C000 ; C999 C306 ;
- [005] 018 ; D01 F16 F62 F51 D63 D61-R D19 D18 D60 ; A999 A486-R ;
A999 A771 ; A999 A511 A486 ;